

November 26, 2013

**COUGAR® LP:**

**COMPRESSION STRENGTH**

Cougar LP's compressive strength was tested and measured at 10% deflection.

Here's how Cougar LP compared with our previous Cougar ridge vent:

Cougar LP was 113% or 2.13 times more compression resistant than previous Cougar.

Here's how Cougar LP compared with Roof Saver ridge vent:

Cougar LP was 347% or 4.47 times more compression resistant than Roof Saver.

Here's our compressive strength data:

Product	Compressive Stress at 10% Deflection
Cougar LP	277psf
Cougar	130psf
Roof Saver	62psf

Should you have any questions regarding the information covered in this document or require any further technical assistance, please do not hesitate to contact our Technical Services team at 800-523-5261 or [techsupport@benjaminobdyke.com](mailto:techsupport@benjaminobdyke.com).