



PHYSICAL PROPERTIES  
DATA SHEET

HYDROFLASH® GP

Test	Test Standard	HYDROFLASH® GP Performance
Tensile Strength	ASTM D 882	15.7 lb./in.
Nail Sealing	ASTM D 1970	Pass
Peel Adhesion	ASTM D 3330 F	OSB: 1.81 lb./in. Aluminum: 7.42 lb./in. Vinyl: 8.11 lb./in. Plywood: 1.63 lb./in. Facer: 8.67 lb./in.
Accelerated UV Aging	ASTM G 154 / D 3330 F	11.61 lb./in.
Elevated Temperature	ASTM D 3330 F	10.52 lb./in.
Water Vapor Transmission	ASTM E 96	<0.1 perms

\*Product to comply with / 15% tolerance when evaluated with listed test standard.

AAMA 711 approved

UV rated: 120 days of exposure before cladding installation

Service temperature: -30° F to 200° F

HYDROFLASH® GP packaging information:

- roll length: 82 ft.
- thickness: 14 mils
- roll widths: 2.3", 4", 6", 9", 12"
- shelf life: 2 years

Benjamin Obdyke Incorporated  
400 Babylon Rd, Suite A  
Horsham, PA 19044

www.benjaminobdyke.com  
800.523.5261  
techsupport@obdyke.com