



PHYSICAL PROPERTIES DATA SHEET

BATTEN UV

Test	Test Standard	BATTEN UV Performance
Compression Behavior	ASTM D 6364	Compressive Strength = 477 psi
UV Cycling 336 hours	ASTM G 154	Compressive Strength = 477 psi
Heat Cycling 90 days @170°	ASTM D 3045	Compressive Strength = 477 psi

*Product to comply with +/- 15% tolerance when evaluated with listed test standard.

UV rated: 365 days of exposure before cladding installation

BATTEN UV size information:

- 1.75" width x 8 ft length x 0.375" thick | 0.5 lbs. per strip