

CEDAR BREATHER® ROOF VENTILATION MAT

Test	Test Standard	CEDAR BREATHER® Performance
Thickness	ASTM D 5199	0.285 in.
Weight	ASTM D 3776	287.1 GSM
Tensile Strength	ASTM D 5034	Machine 32.1 lbf Crosswise 27.4 lbf
Short Term Compression	ASTM D 6364 compressive stress at 10% strain	171 lb/SF
Surface Burning Characteristic	ASTM E 84	Flame Spread Index (FSI) = 10 Smoke Developed Index (SDI) = 75 Class A

*Product to comply with \pm 15% tolerance when evaluated with listed test standard.

UV rated: 30 days of exposure before installation of roofing

CEDAR BREATHER® roll information:

- 39" width x 61.5 ft length x 0.285" thick | 12 lbs/roll