



PHYSICAL PROPERTIES  
DATA SHEET

## SLICKER® CLASSIC RAINSCREEN

Test	Test Standard	SLICKER® CLASSIC Performance
Thickness	ASTM D 5199	0.25 in.
Weight	ASTM D 3776	256 GSM
Tensile Strength	ASTM D 5034	Machine 26 lbf Crosswise 32 lbf
Short Term Compression	ASTM D 6364 compressive stress at 10% strain	179 lb/SF
Surface Burning Characteristic	ASTM E 84	Flame Spread Index (FSI) = 15 Smoke Developed Index (SDI) = 50 Class A

\*Product to comply with +/- 15% tolerance when evaluated with listed test standard.

UV rated: 30 days of exposure before cladding installation

**SLICKER® CLASSIC** roll information:

- 39.37" width x 46.5 ft length x ¼" thick | 11 lbs/roll