



PHYSICAL PROPERTIES  
DATA SHEET

# SLICKER® MAX RAINSCREEN

Test	Test Standard	SLICKER® MAX Performance
Thickness	ASTM D 5199	0.241 in.
Weight	ASTM D 3776	364.5 GSM
Tensile Strength	ASTM D 5034	Machine 86.2 lbf Crosswise 85.4 lbf
Short Term Compression	ASTM D 6364 compressive stress at 10% strain	324 lb/SF
Surface Burning Characteristic	ASTM E 84	Class B

\*Product to comply with +/- 15% tolerance when evaluated with listed test standard.

UV rated: 90 days of exposure before cladding installation

**SLICKER® MAX** roll information:

- 39.37" width x 61.5 ft length x ¼" thick | 20 lbs/roll