



PHYSICAL PROPERTIES DATA SHEET

HYDROFLASH®LA

Test	Test Standard	HYDROFLASH®LA Performance
Peel Adhesion Aluminum	ASTM C 794	30 Pli
Peel Adhesion Concrete	ASTM C 795	30 Pli
Tack Free Time	ASTM C 679	2½ - 3 hours
Elongation at Break	ASTM D 412	1400%
Tensile Strength Ultimate	ASTM D 412	180 PSI
Hardness	ASTM D 412 - Shore A	27
Bond Durability Class 50	ASTM C 719	Pass
VOC	ASTM 3960	18 g/L
Sealant Grade	ASTM C 920 Class 50	Type S, Grade S, Use NT, T1, G, A, M & O

*Product to comply with / 15% tolerance when evaluated with listed test standard.

AAMA 714 approved

Compound Technology: Silyl Terminated Polyurethane (STPU)

*CAN NOT be used in contact with asphalt based materials

UV rated: 180 days of exposure before cladding installation

HYDROFLASH®LA packaging information:

- 20 oz. sausage | 2 lbs. | 12/carton
- 10 oz. tube | 1.25 lbs. | 24/carton
- shelf life: 12 months