



PHYSICAL PROPERTIES
DATA SHEET

FLATWRAP® HP

Test	Test Standard	FLATWRAP® HP Performance
Tensile Strength	ASTM D 5034	Machine 75 lbf Crosswise 54 lbf
Hydrostatic Head	AATCC 127	Pass 55cm of water column for 5 hours
Water Vapor Transmission	ASTM E 96	16 perms
Air Permeance	ASTM E 2178	At 75 Pa calculated flow rate: 0.0062 L/(s.m ²)
Surface Burning Characteristic	ASTM E 84	Flame Spread Index (FSI) = 5 Smoke Developed Index (SDI) = 190 Class A

*Product to comply with +/- 15% tolerance when evaluated with listed test standard.

UV rated: 120 days of exposure before cladding installation

FLATWRAP® HP roll information:

- 5 ft width x 100 ft length | 11 lbs/roll
- 9 ft width x 100 ft length | 19 lbs/roll