



PHYSICAL PROPERTIES DATA SHEET

HYDROFLASH® UV+

Test	Test Standard	HYDROFLASH® UV+ Performance
Tensile Strength	ASTM D 882	46.1 lb./in.
Nail Sealing	ASTM D 1970	Pass
Peel Adhesion	ASTM D 3330 F	OSB: 2.5 lb./in. Aluminum: 12.2 lb./in. Vinyl: 12.5 lb./in. Plywood: 6.7 lb./in. Facer: 14.3 lb./in.
Accelerated UV Aging	ASTM G 154 / D 3330 F	15.8 lb./in.
Elevated Temperature	ASTM D 3330 F	15.2 lb./in.
Water Vapor Transmission	ASTM E 96	4 perms

*Product to comply with +/- 15% tolerance when evaluated with listed test standard.

AAMA 711 approved

UV rated: 365 days of exposure before cladding installation

Service temperature: -30° F to 250° F

HYDROFLASH® UV+ packaging information:

- roll length: 82 ft.
- thickness: 16 mils
- roll widths: 2.3", 4", 6", 9"
- shelf life: 2 years