



PHYSICAL PROPERTIES
DATA SHEET

INVISIWRAP® SA

Test	Test Standard	INVISIWRAP® SA Performance
Tensile Strength	ASTM D 5034	Machine 127.3 lbf Crosswise 96.7 lbf
Hydrostatic Head	AATCC 127	Pass 55cm of water column for 5 hours
Water Vapor Transmission	ASTM E 96	10 perms
Air Permeance	ASTM E 2178	At 75 Pa calculated flow rate: 0.009 L/(s.m ²)
Surface Burning Characteristic	ASTM E 84	Flame Spread Index (FSI) = 20 Smoke Developed Index (SDI) = 90 Class A
Nail Sealing	ASTM D 1970	Pass

*Product to comply with +/- 15% tolerance when evaluated with listed test standard.

UV rated: 365 days of exposure before cladding installation

INVISIWRAP® SA roll information:

- 4.75 ft width x 80 ft length | 30 lbs/roll