



PHYSICAL PROPERTIES  
DATA SHEET

**AERONET™**  
**WALL & ROOF VENTILATION MAT**

Test	Test Standard	AERONET™ Performance
Thickness	ASTM D 5199	0.26 in.
Weight	ASTM D 3776	703.1 GSM
Short Term Compression	ASTM D 6364 compressive stress at 10% strain	773.3 lb/SF
Surface Burning Characteristic	ASTM E 84	Flame Spread Index (FSI) = 55 Smoke Developed Index (SDI) = 110 Class B

\*Product to comply with +/- 15% tolerance when evaluated with listed test standard.

UV rated: 120 days of exposure before cladding installation

AERONET™ roll information:

- 39.4" width x 61 ft length x ¼" thick | 21 lbs/roll