

**BENWRAP™ SA  
SELF-ADHERED WRB HOUSEWRAP**

Test	Test Standard	<b>BENWRAP™ SA</b> Performance
Tensile Strength	ASTM D 5034	Machine 64.3 lbf Crosswise 92.7 lbf
Hydrostatic Head	AATCC 127	Pass 55cm of water column for 5 hours
Water Vapor Transmission	ASTM E 96	14 perms
Air Permeance	ASTM E 2178	At 75 Pa calculated flow rate: 0.0015 L/(s.m <sup>2</sup> )
Surface Burning Characteristic	ASTM E 84	Flame Spread Index (FSI) = 5 Smoke Developed Index (SDI) = 5 Class A
Nail Sealing	ASTM D 1970	Pass

\*Product to comply with / 15% tolerance when evaluated with listed test standard.

UV rated: 120 days of exposure before cladding installation

**BENWRAP™ SA** roll information:

- 4.75 ft width x 80 ft length | 34 lbs/roll